



## PRODUCT DATA SHEET

Date: 05/14/2024

**Spinnaker**  
550 Summit Avenue  
Troy, Oh 45373  
800 543-9452

### 2.3 mil TC White Polypropylene \*\* GPR™. \*\* 40# liner

Item#: 0041930

#### Recommended Print Type(s) to Test

EFI™ Jetrion® (UV Inkjet)

Flexo

---

Facestock: **2.3 mil TC White Polypropylene**

A glossy white, biaxially-oriented polypropylene designed with a unique top coating to be compatible with water-based and solvent-based inks.

Basis Weight:

#### Typical Value

39 #/3300 ft<sup>2</sup>

Caliper:

2.3 mils

Tensile MD/CD:

26,800 / 22,500 PSI

Elongation @ Break MD/TD:

80 / 100%

Opacity:

80%

---

Adhesive: **GPR™.**

A general purpose acrylic removable adhesive designed to remove cleanly from a wide variety of substrates. It is engineered to give excellent tack with minimal building of adhesion over time from a variety of surfaces. It is appropriate for laser applications..

Coat Weight:

#### Typical Value

15 #/3300 ft<sup>2</sup>

Coat Weight:

22.2 grams/m<sup>2</sup>

Caliper:

.6 mils

Adhesion to Stainless Steel, oz. (90° Peel):

13

Loop Tack, oz.:

24

Service Temperature:

-40 to 200 °F

Minimum Application Temperature:

40 °F

Shear (1000g):

35 minutes

---

Release Liner: **40# liner**

A bleached, calendered liner featuring excellent die cutting and stripping characteristics. Recommended for use in roll-to-roll applications.

	<b>Typical Value</b>
Basis Weight:	41 #/3000 ft <sup>2</sup>
Caliper:	2.5 mils
Tensile MD/CD:	34 / 21 #/inch
Tear MD/CD:	34 / 36 grams
Opacity:	69 max%

**Total Product Caliper:** 5.4 mils

**Product Basis Weight Per MMSI:** 208.63 #

**Shelf Life:** 12 month(s) when stored at 72° F, 50% RH

*For application recommendations call 877-210-5104*

*For samples or other questions please call your Sales Representative.*

**Important Notice**

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(\*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 04/05/2018