

## PRODUCT DATA SHEET

Date: 05/14/2024

**Spinnaker** 550 Summit Avenue Troy, Oh 45373 800 543-9452

iGOTM Semi Gloss \*\* XYZTM (2020) \*\* 40# liner

Item#: 0049222

TRIMLESS PROGRAMS			
Dist. Ctr	Length	Min. Width	Core
Troy, Ohio	2.5 K	3"	3"
Troy, Ohio	5 K	3"	3"
Atlanta	2.5 K	3"	3"
Atlanta	5 K	3"	3"

TOTAL EGG DD O GD A MG

Facestock: **iGO**<sup>TM</sup> **Semi Gloss** This glossy, white HP Indigo-ready 55# Semi Gloss is top-coated

for excellent adhesion of HP Indigo liquid ink to the facestock.

This facestock is not recommended for wet applications.

**Typical Value** 

Basis Weight:  $55 \#/3300 \text{ ft}^2$  Caliper: 3.2 mils Tensile MD/CD: 25 / 17 #/inch

Gloss: 62%

Tear MD/CD: 45 / 49 grams

Opacity: 89%

Parker Print: 1.0 microns

Brightness: 87%

Adhesive: **XYZ**<sup>TM</sup> (2020) A general purpose acrylic adhesive for paper facestocks, featuring excellent

ultimate adhesion to polypropylene, polyethylene, and glass. Also appropriate for cylindrical labeling such as test tubes, vials, etc with the appropriate

facestock. May allow for open time with some substrates.

**Typical Value** 

Coat Weight:  $13 \#/3300 \text{ ft}^2$ Coat Weight:  $19.24 \text{ grams/m}^2$ 

Caliper: .6 mils Adhesion to Stainless Steel, oz. (90° Peel): 31 Loop Tack, oz.: 51

Service Temperature: -40 to 240 °F

Minimum Application Temperature: 15 °F

Shear (1000g): 112 minutes

Release Liner: 40# liner A bleached, calendered liner featuring excellent die cutting and stripping

characteristics. Recommended for use in roll-to-roll applications.

**Typical Value** 

 Basis Weight:
 41 #/3000 ft²

 Caliper:
 2.5 mils

 Tensile MD/CD:
 34 / 21 #/inch

 Tear MD/CD:
 34 / 36 grams

 Opacity:
 69 max%

**Total Product Caliper:** 6.3 mils

Product Basis Weight Per MMSI: 238.11#

**Shelf Life:** 12 month(s) when stored at 72° F, 50% RH

For application recommendations call 877-210-5104 For samples or other questions please call your Sales Representative.

## **Important Notice**

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(\*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 05/23/2023