

## PRODUCT DATA SHEET

Date: 05/14/2024

**Spinnaker** 550 Summit Avenue Troy, Oh 45373 800 543-9452

## Semi Gloss for Screen \*\* ATP<sup>TM</sup> \*\* 40# liner

Item#: 0046185

Recommended Print Type(s) to Test	TRIMLESS PROGRAMS			
	Dist. Ctr	Length	Min. Width	Core
Screen Americas (UV Inkjet)	Troy, Ohio	5 K	3"	3"
	Troy, Ohio	10 K	4"	3"
	Atlanta	2.5 K	3"	3"
	Atlanta	5 K	3"	3"
	Ontario, CA	5 K	3"	3"
	Ontario CA	10 K	4"	3"

Facestock: **Semi Gloss for Screen** This glossy, white top-coated 55# Semi Gloss is appropriate for

Screen Americas UV inkjet printing. This facestock is not

TODAY EGG DD O CD A MG

recommended for wet applications.

**Typical Value** 

 Basis Weight:
 55 #/3300 ft²

 Caliper:
 3.1 mils

 Tensile MD/CD:
 25 / 17

 Gloss:
 70%

Tear MD/CD: 49 / 49 grams

Opacity: 87%

Parker Print: 1.0 microns

Brightness: 87%

Adhesive: **ATP**<sup>TM</sup> An all-temperature permanent acrylic adhesive suitable for a wide variety of

applications with paper facestocks providing exceptional converting

characteristics that allow stripping of intricate die patterns as well as wide-web,

high-speed processing.

**Typical Value** 

Coat Weight:  $15 \#/3300 \text{ ft}^2$ Coat Weight:  $22.2 \text{ grams/m}^2$ 

Caliper: .6 mils Adhesion to Stainless Steel, oz. (90° Peel): 20 Loop Tack, oz.: 41

Service Temperature: -65 to 200 °F Minimum Application Temperature: -20 °F Shear (1000g): 61 minutes Release Liner: 40# liner A bleached, calendered liner featuring excellent die cutting and stripping

characteristics. Recommended for use in roll-to-roll applications.

For application recommendations call 877-210-5104

For samples or other questions please call your Sales Representative.

**Typical Value** 

41 #/3000 ft<sup>2</sup> Basis Weight: Caliper: 2.5 mils Tensile MD/CD: 34 / 21 #/inch Tear MD/CD: 34 / 36 grams Opacity: 69 max%

**Total Product Caliper:** 6.2 mils **Product Basis Weight Per MMSI:** 242.32 #

**Shelf Life:** 12 month(s) when stored at 72° F, 50% RH

**Important Notice** 

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(\*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 04/05/2018