



PRODUCT DATA SHEET

Date: 05/14/2024

Spinnaker
550 Summit Avenue
Troy, Oh 45373
800 543-9452

Veero™ 54# Semi Gloss ** VA-365 ** Bloom hi-impact®

Item#: 0050153

Facestock: **Veero™ 54# Semi Gloss**

A bright white, semi gloss litho with excellent strength characteristics. This sheet is printable with UV and water-based flexo, and UV letterpress inks. The lower basis weight creates an economical sheet, without sacrificing quality. This component is not available for custom constructions.

Typical Value

Basis Weight:	54.0 #/3300 ft ²
Caliper:	2.9 mils
Tensile MD/CD:	28 / 15 #/inch
Gloss:	67%
Tear MD/CD:	45 / 55 grams
Opacity:	85.5%
Sheffield Smoothness:	18 SFU
Brightness:	89.8%

Adhesive: **VA-365**

An economical all-temperature acrylic adhesive choice for a wide range of application temperatures. This component is not available for custom constructions.

Typical Value

Coat Weight:	12.5 #/3300 ft ²
Coat Weight:	18.5 grams/m ²
Caliper:	.4 mils
Adhesion to Stainless Steel, oz. (90° Peel):	28
Loop Tack, oz.:	50
Service Temperature:	-65 to 200 °F
Minimum Application Temperature:	-20 °F

Release Liner: **Bloom hi-impact®**

A1.6mil glassine liner that is excellent for die cutting, stripping and label dispensing. Primarily for roll-to-roll applications.

Basis Weight:

Typical Value
27.7 #/3000 ft²

Caliper:

1.6 mils

Tensile MD/CD:

23 / 9 #/inch

Tear MD/CD:

28 / 29 grams

Total Product Caliper: 4.9 mils

Product Basis Weight Per MMSI: 204.15 #

Shelf Life: 12 month(s) when stored at 72° F, 50% RH

For application recommendations call 877-210-5104

For samples or other questions please call your Sales Representative.

Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 05/02/2023