

PRODUCT DATA SHEET

Date: 05/14/2024

Spinnaker

550 Summit Avenue Troy, Oh 45373 800 543-9452

3.0 mil TC Matte White Polypropylene ** B-92 ** 50# liner

Item#: 0041923

Recommended Print Type(s) to Test Thermal Transfer Films Flexo	TRIMLESS PROGRAMS			
	Dist. Ctr	Length	Min. Width	Core
	Troy, Ohio	5 K	3"	3"
	Troy, Ohio	10 K	4"	3"
	New York	5 K	3"	3"
	New York	10 K	4"	3"
	Atlanta	5 K	3"	3"
	Atlanta	10 K	4"	3"
	Chicago	5 K	3"	3"
	Chicago	10 K	4"	3"

Recommended for hand-applied applications only.

Facestock: 3.0 mil TC Matte White Polypropylene	A white, mineral-filled, biaxially-oriented polypropylene film for use in a variety of printing and converting applications where durability, strength, and superior printability are key. One side is matte with a special print-receptive coating and the other is a satin gloss. Its key attribute is excellent thermal transfer printability. It will not tear unless an edge is nicked. Outdoor durability is about 3 to 6 months, depending on climatic conditions.
Pasie Weight	Typical Value 42.5 #/3300 ft ²
Basis Weight: Caliper:	3.0 mils
Tensile MD/CD:	11352 / 17028 PSI
Elongation @ Break MD/TD:	131 / 34%
Opacity:	87%

Adhesive: B-92

An aggressive general-purpose removable adhesive with medium initial tack. It will act as a permanent on smooth surfaces over long time periods or when used with paper facestocks.

Typical Value 15 #/3300 ft² 22.2 grams/m²

Coat Weight: Coat Weight: Caliper:.6 milsAdhesion to Stainless Steel, oz. (90° Peel):22 ozLoop Tack, oz.:41 ozService Temperature:-40 to 200 °FMinimum Application Temperature:40 °FShear (1000g):15 minutes

Release Liner: 50# liner

A bleached, calendered liner featuring higher tensile and tear properties than the 40# liner, making it an excellent liner for perforating, fan-folding, and edge-punching.

Basis Weight: Caliper: Tensile MD/CD: Tear MD/CD: Opacity:

Typical Value

53 #/3000 ft² 3.2 mils 48 / 26 #/inch 45 / 51 grams 74%

Total Product Caliper: 6.8 mils **Product Basis Weight Per MMSI:** 243.79 # **Shelf Life:** 12 month(s) when stored at 72° F, 50% RH For application recommendations call 877-210-5104 For samples or other questions please call your Sales Representative.

Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 04/11/2024