



PRODUCT DATA SHEET

Date: 05/13/2024

Spinnaker
 550 Summit Avenue
 Troy, Oh 45373
 800 543-9452

2.0 mil TC Clear Polypropylene ** GPR™. ** 40# liner

Item#: 0044953

Recommended Print Type(s) to Test	----- TRIMLESS PROGRAMS -----			
	Dist. Ctr	Length	Min. Width	Core
Domino (UV Inkjet)	Troy, Ohio	2.5 K	3"	3"
Durst US (UV inkjet)	Troy, Ohio	5 K	3"	3"
EFI™ Jetrion® (UV Inkjet)	Ontario, CA	2.5 K	3"	3"
Screen Americas (UV Inkjet)	Ontario, CA	5 K	3"	3"
Flexo				

Recommended for hand-applied applications only.

Facestock: 2.0 mil TC Clear Polypropylene

A biaxially-oriented film designed for prime label applications. Its acrylic top coat was specifically engineered for flexo ink receptivity.

	Typical Value
Basis Weight:	31.5 #/3300 ft ²
Caliper:	2.0 mils
Tensile MD/CD:	30,450 / 24,650 PSI
Elongation @ Break MD/TD:	80 / 100%
Gloss:	90 / N/A%
Haze:	2.5%

Adhesive: GPR™.

A general purpose acrylic removable adhesive designed to remove cleanly from a wide variety of substrates. It is engineered to give excellent tack with minimal building of adhesion over time from a variety of surfaces. It is appropriate for laser applications..

	Typical Value
Coat Weight:	15 #/3300 ft ²
Coat Weight:	22.2 grams/m ²
Caliper:	.6 mils
Adhesion to Stainless Steel, oz. (90° Peel):	13
Loop Tack, oz.:	24
Service Temperature:	-40 to 200 °F
Minimum Application Temperature:	40 °F

Shear (1000g):

35 minutes

Release Liner: **40# liner**

A bleached kraft liner featuring excellent die cutting and stripping characteristics.

Typical Value

Basis Weight:

39.6 #/3000 ft²

Caliper:

2.5 mils

Tensile MD/CD:

35 / 15 #/inch

Tear MD/CD:

42 / 48 grams

Opacity:

64%

Total Product Caliper: 5.1 mils

Product Basis Weight Per MMSI: 189.60 #

Shelf Life: 12 month(s) when stored at 72° F, 50% RH

For application recommendations call 877-210-5104

For samples or other questions please call your Sales Representative.

Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 05/23/2023