

PRODUCT DATA SHEET

Date: 05/14/2024

Spinnaker 550 Summit Avenue Troy, Oh 45373 800 543-9452

Semi Gloss for EFITM Jetrion® ** BC-20TM ** 40# liner

Item#: 0043393

Recommended Print Type(s) to Test	TRIMLESS PROGRAMS			
	Dist. Ctr	Length	Min. Width	Core
EFI™ Jetrion® (UV Inkjet)	Troy, Ohio	2.5 K	3"	3"
	Troy, Ohio	5 K	3"	3"
	Troy, Ohio	10 K	4"	3"
	Atlanta	2.5 K	3"	3"
	Atlanta	5 K	3"	3"
	Atlanta	10 K	4"	3"
	Chicago	2.5 K	3"	3"
	Chicago	5 K	3"	3"
	Chicago	10 K	4"	3"
	Ontario, CA	2.5 K	3"	3"
	Ontario, CA	5 K	3"	3"
	Ontario, CA	10 K	4"	3"

Facestock: Semi Gloss for EFITM Jetrion®

This glossy, white top-coated 55# Semi Gloss is appropriate for EFI-Jetrion UV inkjet printing. This facestock is not recommended for wet applications.

Typical Value 55 #/3300 ft²

Basis Weight: Caliper: 3.1 mils Tensile MD/CD: 25 / 17 Gloss: 70% Tear MD/CD: 49 / 49 grams

Opacity: 87% Parker Print: 1.0 microns 87%

Brightness:

Adhesive: BC-20TM A cold temperature hot melt adhesive featuring excellent adhesion to a variety

of packaging materials and other substrates over a wide temperature range. It displays good die cutting and stripping characteristics. This adhesive performs

well on wet and oily/greasy applications.

Typical Value

14 #/3300 ft² Coat Weight: Coat Weight: 20.72 grams/m² Caliper: .6 mils Adhesion to Stainless Steel, oz. (90° Peel): 38 Loop Tack, oz.: 72

Service Temperature: -50 to 145 °F

Minimum Application Temperature: 10 °F Shear (1000g): 157 minutes

Release Liner: 40# liner A bleached, calendered liner featuring excellent die cutting and stripping

characteristics. Recommended for use in roll-to-roll applications.

For samples or other questions please call your Sales Representative.

Typical Value

Basis Weight: $41 \#/3000 \text{ ft}^2$ Caliper: 2.5 mils Tensile MD/CD: 34 / 21 #/inch Tear MD/CD: 34 / 36 grams Opacity: 69 max%

Total Product Caliper: 6.2 mils For application recommendations call 877-210-5104

Product Basis Weight Per MMSI: 240.21 #

Shelf Life: 12 month(s) when stored at 72° F. 50% RH

Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 03/08/2023