



PRODUCT DATA SHEET

Date: 05/13/2024

Spinnaker
 550 Summit Avenue
 Troy, Oh 45373
 800 543-9452

58# Primeglos™ ** SureLock™ ** 40# liner

Item#: 0048572

----- TRIMLESS PROGRAMS -----

Dist. Ctr	Length	Min. Width	Core
Troy, Ohio	2.5 K	3"	3"
Troy, Ohio	5 K	3"	3"
Troy, Ohio	10 K	4"	3"
New York	2.5 K	3"	3"
New York	5 K	3"	3"
New York	10 K	4"	N/A
Chicago	2.5 K	3"	3"
Chicago	5 K	3"	3"
Chicago	10 K	4"	3"
Ontario, CA	2.5 K	3"	3"
Ontario, CA	5 K	3"	3"
Ontario, CA	10 K	4"	N/A

Facestock: **58# Primeglos™**

A 58# bright white sheet featuring high CD tensile and MD tear, great die cutting and stripping characteristics, and good stiffness for dispensing. Low Parker Print and exceptional gloss make this sheet printable with all standard flexo and letterpress inks.

Typical Value

Basis Weight:	58 #/3300 ft ²
Caliper:	3.0 mils
Tensile MD/CD:	35 / 18 #/inch
Gloss:	72%
Tear MD/CD:	43 / 56 grams
Opacity:	88.5%
Parker Print:	.9 microns
Brightness:	90%

Adhesive: **SureLock™**

A hot melt adhesive exhibiting high tack and appropriate flow to aid in many hard-to-stick textured applications. It converts with less build up on press than many other higher coat weight competitors and also provides a flat release profile for good dispensing.

Typical Value

Coat Weight:	17 #/3300 ft ²
--------------	---------------------------

Coat Weight:	25.16 grams/m ²
Caliper:	.8 mils
Adhesion to Stainless Steel, oz. (90° Peel):	70.61 oz
Loop Tack, oz.:	97.84 oz
Service Temperature:	-50 to 140 °F
Minimum Application Temperature:	25 °F

Release Liner: **40# liner** A bleached, calendered liner featuring excellent die cutting and stripping characteristics. Recommended for use in roll-to-roll applications.

	Typical Value
Basis Weight:	41 #/3000 ft ²
Caliper:	2.5 mils
Tensile MD/CD:	34 / 21 #/inch
Tear MD/CD:	34 / 36 grams
Opacity:	69 max%

Total Product Caliper: 6.3 mils
Product Basis Weight Per MMSI: 252.84 #
Shelf Life: 12 month(s) when stored at 72° F, 50% RH

*For application recommendations call 877-210-5104
For samples or other questions please call your Sales Representative.*

Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facstock unless denoted with an asterisk(*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 08/31/2023