



PRODUCT DATA SHEET

Date: 05/13/2024

Spinnaker
 550 Summit Avenue
 Troy, Oh 45373
 800 543-9452

2.2mil Matte White Polyester ** Cryogenic ** 63# Kraft

Item#: 0049943

----- TRIMLESS PROGRAMS -----

Dist. Ctr	Length	Min. Width	Core
Troy, Ohio	2 K	3"	3"

Facestock: **2.2mil Matte White Polyester**

2.2mil matte polyester that show excellent performance in cryogenic applications. This product prints well on conventional print methods and laser. This product can also Thermal Transfer print when paired with the appropriate ribbon. Testing is always recommended. This component is not available for custom constructions.

Typical Value

Basis Weight:	40.9 #/3300 ft ²
Caliper:	2.17 mils
Tensile MD/CD:	80 / 90 MPa
Elongation @ Break MD/TD:	60 / 15%
Gloss:	2.5 / N/A%
Opacity:	91.2%

Adhesive: **Cryogenic**

A high tack solvent acrylic with excellent adhesion to small diameter test tubes and ampules. This adhesive resists edge lifting when repeatedly subjected to changes between extremely low temps and room temp, such as removal from liquid nitrogen. This component is not available for custom constructions.

Typical Value

Caliper:	.9 mils
Adhesion to Stainless Steel, oz. (90° Peel):	37
Loop Tack, oz.:	68
Service Temperature:	-320 to 248 °F
Minimum Application Temperature:	39 °F
Shear (1000g):	551 minutes

Release Liner: **63# Kraft**

This ivory kraft liner is polyethylene laminated on one side. Excellent for die cutting and stripping. This liner is designed for roll to sheet lay-flat applications.

Basis Weight:

Typical Value

63 #/3000 ft²

Caliper:

4.7 mils

Tensile MD/CD:

39 / 28 #/inch

Tear MD/CD:

60 / 60 grams

Opacity:

79.8%

Total Product Caliper: 7.77 mils

For application recommendations call 877-210-5104

Product Basis Weight Per MMSI: 232.00 #

For samples or other questions please call your Sales Representative.

Shelf Life: 12 month(s) when stored at 72° F, 50% RH

Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 05/22/2023