



**PRODUCT DATA SHEET**

Date: 05/14/2024

**Spinnaker**  
 550 Summit Avenue  
 Troy, Oh 45373  
 800 543-9452

**1.5 mil Transparent Polystyrene \*\* BC-20™ \*\* 40# liner**

Item#: 0041880

Recommended Print Type(s) to Test	----- TRIMLESS PROGRAMS -----			
	Dist. Ctr	Length	Min. Width	Core
Flexo	Troy, Ohio	5 K	3"	3"
	Troy, Ohio	10 K	4"	3"
	Chicago	5 K	3"	3"
	Chicago	10 K	4"	3"

Facestock: **1.5 mil Transparent Polystyrene**

A clear, rigid film used for prime label applications. This product is corona-treated for better printing and is appropriate for coupon technology.

	<b>Typical Value</b>
Basis Weight:	27 #/3300 ft <sup>2</sup>
Caliper:	1.5 mils
Tensile MD/CD:	10,500 / 10,500 PSI
Elongation @ Break MD/TD:	45 / 40%
Gloss:	165 / N/A%
Surface Energy:	60 dynes/cm

Adhesive: **BC-20™**

A cold temperature hot melt adhesive featuring excellent adhesion to a variety of packaging materials and other substrates over a wide temperature range. It displays good die cutting and stripping characteristics. This adhesive performs well on wet and oily/greasy applications.

	<b>Typical Value</b>
Coat Weight:	14 #/3300 ft <sup>2</sup>
Coat Weight:	20.72 grams/m <sup>2</sup>
Caliper:	.6 mils
Adhesion to Stainless Steel, oz. (90° Peel):	38
Loop Tack, oz.:	72
Service Temperature:	-50 to 145 °F
Minimum Application Temperature:	10 °F
Shear (1000g):	157 minutes

---

Release Liner: **40# liner**

A bleached, calendered liner featuring excellent die cutting and stripping characteristics. Recommended for use in roll-to-roll applications.

Basis Weight:

**Typical Value**  
41 #/3000 ft<sup>2</sup>

Caliper:

2.5 mils

Tensile MD/CD:

34 / 21 #/inch

Tear MD/CD:

34 / 36 grams

Opacity:

69 max%

**Total Product Caliper:** 4.6 mils

**Product Basis Weight Per MMSI:** 181.26 #

**Shelf Life:** 12 month(s) when stored at 72° F, 50% RH

*For application recommendations call 877-210-5104*

*For samples or other questions please call your Sales Representative.*

**Important Notice**

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(\*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 05/22/2023