



PRODUCT DATA SHEET

Date: 05/13/2024

Spinnaker
 550 Summit Avenue
 Troy, Oh 45373
 800 543-9452

2.4m White Pearlized BOPP ** VA-365 ** 40# BWG

Item#: 0048468

----- TRIMLESS PROGRAMS -----

Dist. Ctr	Length	Min. Width	Core
Chicago	2.5 K	3"	3"
Chicago	5 K	3"	3"
Chicago	10 K	4"	3"
Ontario, CA	2.5 K	3"	3"
Ontario, CA	5 K	3"	3"
Ontario, CA	10 K	4"	3"

Facestock: **2.4m White Pearlized BOPP**

A top coated white polypropylene film with a pearlized appearance. This product offers excellent flexo printability. We have also had success with thermal transfer printing using resin and wax/resin ribbons. Testing is recommended with your specific printer and ribbon combinations. This component is not available for custom constructions.

Basis Weight:
 Caliper:
 Gloss:
 Opacity:

Typical Value
 30 #/3300 ft²
 2.4 mils
 95 / N/A%
 89%

Adhesive: **VA-365**

An economical all-temperature acrylic adhesive choice for a wide range of application temperatures. This component is not available for custom constructions.

Coat Weight:
 Coat Weight:
 Caliper:
 Adhesion to Stainless Steel, oz. (90° Peel):
 Loop Tack, oz.:
 Service Temperature:
 Minimum Application Temperature:

Typical Value
 12.5 #/3300 ft²
 18.5 grams/m²
 .4 mils
 28
 50
 -65 to 200 °F
 -20 °F

Release Liner: **40# BWG**

An economical 40# bleached glassine white liner that offers excellent roll label converting properties. This component is not available for custom constructions.

Basis Weight:

Typical Value

38 #/3000 ft²

Caliper:

2.2 mils

Tensile MD/CD:

34 / 17 #/inch

Tear MD/CD:

28 / 31 grams

Opacity:

56%

Total Product Caliper: 5 mils

Product Basis Weight Per MMSI: 177.47 #

Shelf Life: 12 month(s) when stored at 72° F, 50% RH

For application recommendations call 877-210-5104

For samples or other questions please call your Sales Representative.

Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 05/23/2023