

# PRODUCT DATA SHEET

Date: 04/30/2025

**Spinnaker** 550 Summit Avenue Troy, Oh 45373 800 543-9452

## Semi Gloss for Domino \*\* XYZ<sup>TM</sup> (2020) \*\* 40# liner

Item#: 0049224

	TRIMLESS PROGRAMS			
	Dist. Ctr	Length	Min. Width	Core
	Troy, Ohio	2.5 K	3"	3"
	Troy, Ohio	5 K	3"	3"
	Atlanta	2.5 K	3"	3"
	Atlanta	5 K	3"	3"
Facestock: Semi Gloss for Domino	This glossy, white top-coated 55# Semi Gloss is appropriate for			
	Domino UV in	kjet printing.	This facestock is not	recommended
	for wet application	tions.		
	<b>T</b>			
	Typical Value			
Basis Weight:	55 #/3300 ft <sup>2</sup>			
Caliper:	3.1 mils			
Tensile MD/CD:	25 / 17 #/inch			
Gloss:	70%			
Tear MD/CD:	49 / 49 grams			
Opacity:	87%			
Parker Print:	1.0 microns			
Brightness:	87%			

Adhesive: <b>XYZ<sup>TM</sup> (2020)</b>	A general purpose acrylic adhesive for paper facestocks, featuring excellent ultimate adhesion to polypropylene, polyethylene, and glass. Also appropriate for cylindrical labeling such as test tubes, vials, etc with the appropriate facestock. May allow for open time with some substrates.
	Typical Value
Coat Weight:	13 #/3300 ft <sup>2</sup>
Coat Weight:	19.24 grams/m <sup>2</sup>
Caliper:	.6 mils
Adhesion to Stainless Steel, oz. (90° Peel):	31
Loop Tack, oz.:	51
Service Temperature:	-40 to 240 °F
Minimum Application Temperature:	15 °F
Shear (1000g):	112 minutes

#### Release Liner: 40# liner

A bleached, calendered liner featuring excellent die cutting and stripping characteristics. Recommended for use in roll-to-roll applications.

Basis Weight: Caliper: Tensile MD/CD: Tear MD/CD: Opacity: **Typical Value** 41 #/3000 ft<sup>2</sup> 2.5 mils 34 / 21 #/inch 34 / 36 grams 69 max%

### **Total Product Caliper:** 6.2 mils **Product Basis Weight Per MMSI:** 238.11 # **Shelf Life:** 12 month(s) when stored at 72° F, 50% RH

For application recommendations call 877-210-5104 For samples or other questions please call your Sales Representative.

#### **Important Notice**

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(\*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 05/23/2023