

PRODUCT DATA SHEET

Date: 05/10/2024

Spinnaker 550 Summit Avenue Troy, Oh 45373 800 543-9452

45# CTT ** SureLockTM ** 40# liner

Item#: 0042834

Recommended Print Type(s) to Test	TRIMLESS PROGRAMS			
	Dist. Ctr	Length	Min. Width	Core
Screen Americas (UV Inkjet) Thermal Transfer Papers Flexo	Troy, Ohio	2.5 K	3"	3"
	Troy, Ohio	5 K	3"	3"
	Troy, Ohio	10 K	4"	3"
	New York	2.5 K	3"	3"
	New York	5 K	3"	3"
	New York	10 K	4"	3"
	Atlanta	2.5 K	3"	3"
	Atlanta	5 K	3"	3"
	Atlanta	10 K	4"	3"
	Chicago	2.5 K	3"	3"
	Chicago	5 K	3"	3"
	Chicago	10 K	4"	3"
	Ontario, CA	2.5 K	3"	3"
	Ontario, CA	5 K	3"	3"
	Ontario CA	10 K	4"	3"

Facestock: 45# CTT

A premium, coated sheet that has excellent thermal transfer imaging with a wide range of ribbons, and superior flexo printability.

Typical Value

 Basis Weight:
 45 #/3300 ft²

 Caliper:
 3.0 mils

 Tensile MD/CD:
 27 / 17

 Tear MD/CD:
 42 / 45 grams

 Opacity:
 88%

 Brightness:
 87%

Adhesive: SureLockTM

A hot melt adhesive exhibiting high tack and appropriate flow to aid in many hard-to-stick textured applications. It converts with less build up on press than many other higher coat weight competitors and also provides a flat release profile for good dispensing.

Typical Value

Coat Weight: 17 #/3300 ft² Coat Weight: 25.16 grams/m² Caliper: .8 mils
Adhesion to Stainless Steel, oz. (90° Peel): 70.61 oz
Loop Tack, oz.: 97.84 oz
Service Temperature: -50 to 140 °F
Minimum Application Temperature: 25 °F

Release Liner: 40# liner A bleached, calendered liner featuring excellent die cutting and stripping

characteristics. Recommended for use in roll-to-roll applications.

Typical Value

 Basis Weight:
 41 #/3000 ft²

 Caliper:
 2.5 mils

 Tensile MD/CD:
 34 / 21 #/inch

 Tear MD/CD:
 34 / 36 grams

 Opacity:
 69 max%

Total Product Caliper: 6.3 mils

Product Basis Weight Per MMSI: 225.47 #

Shelf Life: 12 month(s) when stored at 72° F, 50% RH

For application recommendations call 877-210-5104 For samples or other questions please call your Sales Representative.

Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 10/05/2023