



## PRODUCT DATA SHEET

Date: 05/10/2024

**Spinnaker**  
550 Summit Avenue  
Troy, Oh 45373  
800 543-9452

### Smudgeproof Kimdura® FPG-80 \*\* C-122F \*\* 50# liner

Item#: 0041915

Recommended Print Type(s) to Test	----- TRIMLESS PROGRAMS -----			
	Dist. Ctr	Length	Min. Width	Core
Impact Films	Troy, Ohio	5 K	3"	3"
Thermal Transfer Films	Troy, Ohio	10 K	4"	3"
Flexo	Chicago	5 K	3"	3"
	Chicago	10 K	4"	3"

This face/adhesive combination conforms to BS5609: 1986 Section 2 - 'Maritime and Laboratory Performance of Label Base Materials for drum labelling.

Facestock: **Smudgeproof Kimdura® FPG-80**

This film is a matte white, multi-layer polypropylene film top-coated to provide premium dot matrix and thermal transfer print images. Outdoor exposure is up to one year. Typical applications include shelf marking and container labeling. The product is no longer warranted for Flexographic or any non-thermal printing methods based on feedback from the facestock supplier.

Basis Weight:

#### Typical Value

56 #/3300 ft<sup>2</sup>

Caliper:

3.8 mils

Tensile MD/CD:

22 / 62 #/inch

Elongation @ Break MD/TD:

89.9 / 16.1%

Opacity:

95%

Adhesive: **C-122F**

A premium drum and barrel acrylic adhesive for film facestocks that provides excellent adhesion to painted metal, polyolefin and fiber drums in all weather conditions. As a heavy coat weight of B-122F, It is well suited for the most demanding of label applications.

Coat Weight:

#### Typical Value

18 #/3300 ft<sup>2</sup>

Coat Weight:

26.64 grams/m<sup>2</sup>

Caliper:

.8 mils

Adhesion to Stainless Steel, oz. (90° Peel):

32.1oz

Loop Tack, oz.:

32.6 oz

Service Temperature:	-65 to 200 °F
Minimum Application Temperature:	-10 °F
Shear (1000g):	82 minutes

---

Release Liner: <b>50# liner</b>	A bleached, calendered liner featuring higher tensile and tear properties than the 40# liner, making it an excellent liner for perforating, fan-folding, and edge-punching.
---------------------------------	---

	<b>Typical Value</b>
Basis Weight:	53 #/3000 ft <sup>2</sup>
Caliper:	3.2 mils
Tensile MD/CD:	48 / 26 #/inch
Tear MD/CD:	45 / 51 grams
Opacity:	74%

**Total Product Caliper:** 7.8 mils  
**Product Basis Weight Per MMSI:** 278.53 #  
**Shelf Life:** 12 month(s) when stored at 72° F, 50% RH

*For application recommendations call 877-210-5104  
For samples or other questions please call your Sales Representative.*

**Important Notice**

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(\*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 02/13/2024