

PRODUCT DATA SHEET

Date: 05/10/2024

Spinnaker 550 Summit Avenue Troy, Oh 45373 800 543-9452

2mil Matte Silver PET ** SFATM ** 50# liner

Item#: 0048054

Dist. Ctr	Length	Min. Width	Core
Troy, Ohio	5 K	3"	3"
Troy, Ohio	2.5 K	3"	3"

----- TRIMLESS PROGRAMS -----

Facestock: 2mil Matte Silver PET

A matte silver polyester film that offers high tear strength, heat resistance, dimensional stability, opacity and chemical resistance. It resists scuff and is appropriate for general durable use. The product shows excellent print characteristics for Flexo and Thermal Transfer printing. This product is not recommended for laser printing.

Typical Value

Basis Weight: $48.6 \#/3300 \text{ ft}^2$ Caliper: 2.1 mils

Tensile MD/CD: 22700 / 29900 PSI

Elongation @ Break MD/TD: 160 / 100%

Opacity: 99%

Adhesive: **SFA**TM A clear, general purpose, emulsion acrylic permanent adhesive designed for

applications with film facestocks. SFA exhibits excellent ultimate adhesion to polyethylene, polypropylene and glass. Well suited for small, cylindrical

labeling and is glove friendly.

Typical Value

Coat Weight: $13 \#/3300 \text{ ft}^2$ Coat Weight: 19.24 grams/m^2

Caliper: .6 mils Adhesion to Stainless Steel, oz. (90° Peel): 27 Loop Tack, oz.: 33

Service Temperature: $-40 \text{ to } +200 \text{ }^{\circ}\text{F}$

Minimum Application Temperature: 40 °F Shear (1000g): 450 minutes Release Liner: 50# liner A bleached, calendered liner featuring higher tensile and tear properties than the

40# liner, making it an excellent liner for perforating, fan-folding, and edge-

punching.

Typical Value

Basis Weight: $53 \#/3000 \text{ ft}^2$ Caliper: 3.2 mils Tensile MD/CD: 48 / 26 #/inch Tear MD/CD: 45 / 51 grams

Opacity: 74%

Total Product Caliper: 5.9 mils

Product Basis Weight Per MMSI: 252.42 #

Shelf Life: 12 month(s) when stored at 72° F, 50% RH

For application recommendations call 877-210-5104 For samples or other questions please call your Sales Representative.

Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 05/04/2020