

PRODUCT DATA SHEET

Date: 05/10/2024

Spinnaker 550 Summit Avenue Troy, Oh 45373 800 543-9452

Laser Latex ** ATPTM ** 3.5 mil (50#) LF

Item#: 0001495

Recommended Print Type(s) to Test Laser Flexo	TRIMLESS PROGRAMS			
	Dist. Ctr	Length	Min. Width	Core
	Troy, Ohio	5 K	3"	6"
	Troy, Ohio	10 K	4"	6"
	Chicago	5 K	3"	6"
	Chicago	10 K	4"	6"

Facestock: Laser Latex A C2S saturated paper designed to have excellent toner receptivity

in a variety of laser printers, while offering the same strength and environmental properties of a typical latex sheet. Common applications include drum labeling and shelf marking.

Typical Value

Basis Weight: 58.2 #/3300 ft²

Caliper: 3.7 mils

Tensile MD/CD: 29.8 / 20.5 #/inch
Tear MD/CD: 45 / 45 grams

Opacity: 87%
Sheffield Smoothness: 60 SFU

Adhesive: **ATP**TM An all-temperature permanent acrylic adhesive suitable for a wide variety of

applications with paper facestocks providing exceptional converting

characteristics that allow stripping of intricate die patterns as well as wide-web,

high-speed processing.

Typical Value

Coat Weight: $15 \#/3300 \text{ ft}^2$ Coat Weight: 22.2 grams/m^2

Caliper: .6 mils Adhesion to Stainless Steel, oz. (90° Peel): 20 Loop Tack, oz.: 41

Service Temperature: -65 to 200 °F Minimum Application Temperature: -20 °F Shear (1000g): 61 minutes Release Liner: 3.5 mil (50#) LF The 3.5mil layflat is a bleached white, MG liner designed specifically to be

compatible with high and medium speed cut-sheet laser and ink jet printers. This product is well suited for applications requiring a high degree of layflat. A small amount of clay is applied to the backside of the paper to enhance printability.

For application recommendations call 877-210-5104

For samples or other questions please call your Sales Representative.

Typical Value

Basis Weight: 50 #/3000 ft2 Caliper: 3.5 mils Tensile MD/CD: 35 / 14 #/inch Tear MD/CD: 50 / 75 grams

89% Opacity:

Total Product Caliper: 7.8 mils

Product Basis Weight Per MMSI: 269.89 #

Shelf Life: 12 month(s) when stored at 72° F, 50% RH

Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 05/22/2023