



PRODUCT DATA SHEET

Date: 05/10/2024

Spinnaker

550 Summit Avenue
Troy, Oh 45373
800 543-9452

Ultra Matte™ Litho ** SC-21 ** 40# liner

Item#: 0041668

Recommended Print Type(s) to Test

Domino (UV Inkjet)
EFI™ Jetrion® (UV Inkjet)
Flexo

----- TRIMLESS PROGRAMS -----

Dist. Ctr	Length	Min. Width	Core
Troy, Ohio	2.5 K	3"	3"
Troy, Ohio	5 K	3"	3"
Troy, Ohio	10 K	4"	3"
Atlanta	2.5 K	3"	3"
Atlanta	5 K	3"	3"
Atlanta	10 K	4"	3"
Chicago	2.5 K	3"	3"
Chicago	5 K	3"	3"
Ontario, CA	2.5 K	3"	3"
Ontario, CA	5 K	3"	3"
Ontario, CA	10 K	4"	3"

Facestock: **Ultra Matte™ Litho**

A premium, matte-coated paper featuring superior smudge resistance, high brightness and high opacity. This sheet offers great ink receptivity, and can also be laser printed.

Typical Value

Basis Weight:	60 #/3300 ft ²
Caliper:	3.7 mils
Tensile MD/CD:	35 / 17
Gloss:	10%
Tear MD/CD:	50 / 55 grams
Opacity:	91%
Sheffield Smoothness:	30 SFU
Parker Print:	2.8 microns
Brightness:	89%

Adhesive: **SC-21**

A robust hot-melt adhesive exhibiting excellent adhesion and quick tack to a broad range of surfaces over a wide application temperature range. It displays the superior converting characteristics of an acrylic and wide web converting is excellent.

Typical Value

Coat Weight:	14 #/3300 ft ²
Coat Weight:	20.72 grams/m ²

Caliper:	.6 mils
Adhesion to Stainless Steel, oz. (90° Peel):	48
Loop Tack, oz.:	89
Service Temperature:	-50 to 140 °F
Minimum Application Temperature:	25 °F
Shear (1000g):	1078 minutes

Release Liner: 40# liner	A bleached, calendered liner featuring excellent die cutting and stripping characteristics. Recommended for use in roll-to-roll applications.
---------------------------------	---

	Typical Value
Basis Weight:	41 #/3000 ft ²
Caliper:	2.5 mils
Tensile MD/CD:	34 / 21 #/inch
Tear MD/CD:	34 / 36 grams
Opacity:	69 max%

Total Product Caliper: 6.8 mils
Product Basis Weight Per MMSI: 250.74 #
Shelf Life: 12 month(s) when stored at 72° F, 50% RH

*For application recommendations call 877-210-5104
For samples or other questions please call your Sales Representative.*

Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 05/23/2023