

## PRODUCT DATA SHEET

Date: 05/10/2024

**Spinnaker** 550 Summit Avenue Troy, Oh 45373 800 543-9452

Veero 2.3m TC White Polypropylene (2018) \*\* VG-325 \*\* 40# BWG

Item#: 0048343

Replaces old item# 45246

Facestock: Veero 2.3m TC White Polypropylene

(2018)

A white, biaxially-oriented polypropylene film. The surface has been topcoated to provide superior printability. This facestock has excellent moisture resistance, and good diecutting and dispensing characteristics. This component is not available for custom constructions.

**Typical Value** 

 Basis Weight:
 39 #/3300 ft²

 Caliper:
 2.3 mils

 Gloss:
 96 / N/A%

 Opacity:
 86%

Adhesive: VG-325 A general purpose permanent emulsion acrylic adhesive that offers excellent

adhesion. This component is not available for custom constructions.

**Typical Value** 

Coat Weight:  $13.5 \#/3300 \text{ ft}^2$ Coat Weight:  $19.98 \text{ grams/m}^2$ 

Caliper: .4 mils Adhesion to Stainless Steel, oz. (90° Peel): 33 Loop Tack, oz.: 39

Service Temperature: -40 to 248 °F

Minimum Application Temperature: 25 °F

Release Liner: 40# BWG An economical 40# bleached glassine white liner that offers excellent roll label

converting properties. This component is not available for custom

constructions.

**Typical Value** 

 $\begin{array}{lll} \text{Basis Weight:} & 38 \ \#/3000 \ \text{ft}^2 \\ \text{Caliper:} & 2.2 \ \text{mils} \\ \text{Tensile MD/CD:} & 34 \ / \ 17 \ \#/\text{inch} \\ \text{Tear MD/CD:} & 28 \ / \ 31 \ \text{grams} \\ \end{array}$ 

Opacity: 56%

**Total Product Caliper:** 4.9 mils

Product Basis Weight Per MMSI: 198.53 #

**Shelf Life:** 12 month(s) when stored at 72° F, 50% RH

For application recommendations call 877-210-5104 For samples or other questions please call your Sales Representative.

## **Important Notice**

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(\*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 06/14/2023