

## PRODUCT DATA SHEET

Date: 04/26/2024

Spinnaker 550 Summit Avenue Troy, Oh 45373 800 543-9452

## 2.6 mil TC White Label-Lyte® \*\* B-122<sup>TM</sup>F \*\* 40# liner

Item#: 0041894

Recommended Print Type(s) to Test	TRIMLESS PROGRAMS			
	Dist. Ctr	Length	Min. Width	Core
Flexo	Atlanta	2.5 K	3"	3"
	Atlanta	5 K	3"	3"
	Atlanta	10 K	4"	3"
	Chicago	2.5 K	3"	3"
	Chicago	5 K	3"	3"
	Chicago	10 K	4"	3"
	Ontario, CA	2.5 K	3"	3"
	Ontario, CA	5 K	3"	3"
	Ontario CA	10 K	4"	3"

Facestock: 2.6 mil TC White Label-Lyte®

A white, multi-layer, biaxially-oriented polypropylene film that is top-coated for ink receptivity.

**Typical Value** 

Basis Weight: 33.2 #/3300 ft<sup>2</sup>

Caliper: 2.6 mils

Tensile MD/CD: 12,600 / 22,200 PSI

Elongation @ Break MD/TD: 180 / 45% Opacity: 88%

Adhesive: **B-122**<sup>TM</sup>**F** A clear all temperature acrylic adhesive featuring excellent adhesion to a variety

> of surfaces with film facestocks. It covers a broad temperature range and has excellent converting characteristics on press. The high initial tack of B-122F to

low surface energy polyolefins makes it an ideal for blow on applications

**Typical Value** 

Coat Weight: 13 #/3300 ft<sup>2</sup> Coat Weight: 19.24 grams/m<sup>2</sup>

.6 mils Caliper: Adhesion to Stainless Steel, oz. (90° Peel): 24 Loop Tack, oz.: 47

Service Temperature: -65 to 200 °F -10 °F Minimum Application Temperature: Shear (1000g): 75 minutes

Release Liner: 40# liner A bleached, calendered liner featuring excellent die cutting and stripping

characteristics. Recommended for use in roll-to-roll applications.

**Typical Value** 

 Basis Weight:
 41 #/3000 ft²

 Caliper:
 2.5 mils

 Tensile MD/CD:
 34 / 21 #/inch

 Tear MD/CD:
 34 / 36 grams

 Opacity:
 69 max%

**Total Product Caliper:** 5.7 mils

**Product Basis Weight Per MMSI:** 192.21 #

**Shelf Life:** 12 month(s) when stored at 72° F, 50% RH

For application recommendations call 877-210-5104 For samples or other questions please call your Sales Representative.

## **Important Notice**

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(\*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 05/23/2023