



PRODUCT DATA SHEET

Date: 04/30/2025

Spinnaker
550 Summit Avenue
Troy, Oh 45373
800 543-9452

2.4m TC White BOPP ** VA-365 ** 1.2M Polyester Liner

Item#: 0050345

----- TRIMLESS PROGRAMS -----

Dist. Ctr	Length	Min. Width	Core
Atlanta	2.5 K	3"	3"
Atlanta	5 K	3"	3"
Atlanta	10 K	4"	3"
Ontario, CA	2.5 K	3"	3"
Ontario, CA	5 K	3"	3"
Ontario, CA	10 K	4"	3"

Facestock: **2.4m TC White BOPP**

A white, biaxially-oriented polypropylene film. The surface has been topcoated to provide superior printability. This facestock has excellent moisture resistance, and good diecutting and dispensing characteristics. This component is not available for custom constructions.

Typical Value

Basis Weight:	28.4 #/3300 ft ²
Caliper:	2.36 mils
Tensile MD/CD:	80 / 155 N/15mm
Elongation @ Break MD/TD:	160 / 40%
Opacity:	86%
Surface Energy:	40 dynes/cm

Adhesive: **VA-365**

An economical all-temperature acrylic adhesive choice for a wide range of application temperatures. This component is not available for custom constructions.

Typical Value

Coat Weight:	12.5 #/3300 ft ²
Coat Weight:	18.5 grams/m ²
Caliper:	.4 mils
Adhesion to Stainless Steel, oz. (90° Peel):	28
Loop Tack, oz.:	50
Service Temperature:	-65 to 200 °F
Minimum Application Temperature:	-20 °F

Release Liner: **1.2M Polyester Liner**

A durable 1.2 mil polyester liner suitable for high-speed diecutting and stripping applications. Used primarily for roll-to-roll, high-speed dispensing applications.

Typical Value

Basis Weight:

27.7 #/3000 ft²

Caliper:

1.18 mils

Tensile MD/CD:

21,800 / 21,800 psi

Total Product Caliper: 3.94 mils

Product Basis Weight Per MMSI: 150.25 #

Shelf Life: 12 month(s) when stored at 72° F, 50% RH

For application recommendations call 877-210-5104

For samples or other questions please call your Sales Representative.

Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 09/16/2024